



Chemical Compatibility Guide for: Pipe Repair Tape

NOTICE:

The guide on the following page(s) was provided by the supplier. New Pig Limited assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.

**For additional assistance, please contact New Pig Technical Services
on 0800 919 900.**

100% Money-Back Guarantee

Buy with confidence knowing that everything we sell is backed by our 12-month Money-Back Guarantee! If you're not 100% satisfied with a product, just call one of our Sales and Service Advisors and they'll arrange for a free return and pick-up at no cost to you. We'll refund all VAT, shipping costs and any other incidentals, so there are never any hassles — we'll even take care of all the paperwork!

Hogs Hill, Watt Place, Hamilton International Technology Park, Blantyre G72 0AH • 0800 919 900
Fax: 0800 731 50 71 • Email: pigpen@newpig.com • Web: newpig.co.uk

© New Pig Corporation. All rights reserved.

PIPE REPAIR TAPE - CHEMICAL RESISTANCE GUIDE

KEY **R-** Resistant for continuous immersion
LR- Suitable for occasional splashes/short term contact
NR- Not recommended for any form of contact

ACETALDEHYDE	LR	HYDROCHLORIC ACID less than 10 %	R
ACETIC ACID greater than 20 %	NR	HYDROGEN PEROXIDE LESS THAN	R
ACETONE	LR	KEROSENE	R
ANILINE	LR	LACTIC ACID LESS THAN 20%	R
AVIATION FUEL	R	LINSEED OIL	R
BENZENE	R	LUBRICATING OIL	R
BUTYL ALCOHOL	LR	METHYL ALCOHOL	NR
BUTYL ACETATE	LR	METHYL ETHYL KETONE	LR
CALCIUM CARBONATE	R	METHYLENE CHLORIDE	NR
CARBONIC ACID	R	MOLASSES	R
CARBON TETRACHLORIDE	NR	NAPHTHA	R
CASTER OIL	R	NITRIC ACID less than 10 %	R
CHLOROFORM	LR	PARAFFIN WAX	R
CITRIC ACID LESS THAN 10%	R	PENTANE	R
CREOSOTE	LR	PHENOL	LR
CRUDE OIL	R	PHOSPHORIC ACID less than 10 %	R
CYCLOHEXANONE	LR	PHOSPHORIC ACID less than 20 %	R
DIACETONE ALCOHOL	LR	PHOSPHORIC ACID less than 75%	R
DIBUTYL PHTHALATE	R	POTASSIUM CARBONATE	R
DIESEL OIL	R	POTASSIUM HYDROXIDE 10%	R
DIETHYLENE GLYCOL	R	PYRIDINE	LR
DIETHYLENE TRIAMINE	LR	SODIUM CHLORIDE	R
DISTILLED WATER	R	SODIUM HYDROXIDE	R
ETHYL ALCOHOL	LR	STYRENE	LR
ETHYL ACETATE	LR	SULPHURIC ACID less than 10 %	R
ETHYLENE GLYCOL	R	TOLUENE	LR
FERRIC CHLORIDE	R	TRICHLOROETHYLENE	LR
FORMALDEHYDE	LR	TURPENTINE	R
FORMIC ACID less than 10 %	R	VEGETABLE OIL	R
GASOLINE	R	WHITE SPIRIT	R
GLYCEROL	R	WHISKY	R
HEPTANE	R	WINE	R
HEXANOL	R	XYLENE	LR
		ZINC CHLORIDE	R

Note 1: This table is for guidance purposes only.

Note 2: All products are resistant to aqueous solutions of most chemical salts of inorganic acids